

# BITUMEN 10/20

**B.NO:08010**

Property/Unit	VALUE	TEST Method
Specific Gravity &25/25°c	1.01-1.06	ASTM D70
Penetration & 25°c	10-20	ASTM D5
Softening Point °c	85-95	ASTM D36
Ductility & 25°c	5min	ASTM D113
Loss on heating % wt	0.2 max	ASTM D6
Drop in penetration after heating %	20 max	ASTM D6 & ASTM D5
Flash point °c	225 min	ASTM D92
Solubility in THC %wt	99.5min	ASTM D4
Spot test	Negative	*A.A.S.H.O.T 102