

# BITUMEN 60/70

B.NO:08007

Property/Unit	VALUE	TEST Method
Specific Gravity &25/25°c	1.01-1.060	ASTM D70
Penetration & 25°c	60 – 70	ASTM D5
Softening Point °c	49 – 56	ASTM D36
Ductility & 25°c	100min	ASTM D113
Loss on heating % wt	0.2 max	ASTM D6
Drop in penetration after heating %	20 max	ASTM D6 & ASTM D5
Flash point °c	>250 °C	ASTM D92
Solubility in THC %wt	>99.5	ASTM D4
Spot test	Negative	*A.A.S.H.O.T 102