

# BITUMEN

**B.NO:08001**

<b>ANALYSIS</b>	<b>SPECIFIC</b>	<b>TEST METHOD</b>
Specific gravity @ 25/25-0 °C	1.03-1.1	D – 70
Penetration@25-0°C 5	60-70	D – 5
Sotrening Point °C	42-46	D – 36
Ductility @25°C	100 min	D – 113
Loss on heating (wt)%	0.3 max	D – 6
Drop in penetration after	20 max	D -6 & D – 5
Flash point °C	240 min	D – 92
Solubility in C2 (wt)%	90 min	D – 4
Spot Test	Negative	A.A.S.H.O.T.102*