

# BITUMEN 85/100

B.NO:08008

Property/Unit	VALUE	TEST Method
Specific Gravity &25/25°c	1.01-1.05	ASTM D70
Penetration & 25°c	85 – 100	ASTM D5
Softening Point °c	45 – 52	ASTM D36
Ductility & 25°c	100min	ASTM D113
Loss on heating % wt	0.5 max	ASTM D6
Drop in penetration after heating %	20 max	ASTM D6 & ASTM D5
Flash point °c	225min	ASTM D92
Solubility in THC %wt	99.5min	ASTM D4
Spot test	Negative	*A.A.S.H.O.T 102