

BITUMEN 60/70

B.NO:08006

Property/Unit	Specification	TEST Method
Specific Gravity, 25/25°C	1.01-16	ASTM D70
Penetration, 25 °C , 5	60 – 70	ASTM D5
Sotreninig Point °C	49.56	ASTM D36
Ductility, 25 °C	100 min	ASTM D113
Loss on heating (wt%)	0.2 max	ASTM D6
Drop-in penetration	20 max	ASTM D6 & ASTM D5
Flash point (°C)	250 min	ASTM D92
Solubility in C2 (wt%)	99.5 min	ASTM D4
Spot test	Negative	*A.A.S.H.O.T 102